

TECHNICAL DATA

EVERLAY EG - thickness mm 6,0

10/2010

Rolls: height cm 200, lenght 20 mtl. Weight: 3 kg/m²

<u>GENERAL REQUIREMENTS</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Overall thickness	EN 428	mm	6,0
Mass per unit area	EN 430	g/m ²	3000
Dimensional stability	EN 434	%	0,1
Curling after exposure to heat	EN 434	mm	1
Colour fastness to artificial light	ISO 105-B02 method 3	degree	≥ 6
<u>ESSENTIAL REQUIREMENTS</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Improvement in footfall sound absorption	ISO 140/8 ISO 717/2	dB	15
Thermal resistance	EN 12667	m ² K/W	0,106
Thermal conductivity	EN 12667	W/mK	0,0566
<u>OPTIONAL PROPERTIES</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Shock absorption (glued with Mondoflex 4 mm)	EN 14808	%	27
Shock absorption (glued with Mondosport I 4,5 mm)	EN 14808	%	26

Mondo keeps the right to modify the characteristics of the products in any moment.