

## FORZA 10 mm

Revision # 0 of 03/24/10

<b>Product Description</b>	Prefabricated cardio and fitness rubber flooring. Designed for interior applications, specifically engineered to withstand daily abuse and provide the resiliency needed in fitness centers, locker rooms and rehabilitation areas. Made of the highest quality natural and synthetic rubbers, composed of dual durometer layers calendared and vulcanized together for durability and performance . The top performance layer is non-porous, It provides slip-resistance and strength. The bottom layer consists of post consumer rubber granules especially formulated and engineered to provide high cushioning for underfoot comfort, moderate impact and noise absorption.		
<b>Surface Texture</b>	Sealskin		
<b>Surface Color</b>	Please refer to Mondo's website for available colors		
<b>Roll Width</b>	6' (1.83 m)		
<b>Roll Length</b>	max 39' (12 m)		
<b>Adhesive</b>	Mondo PU 105 Mondo EP 55 (indoor application on concrete subfloors only; not suitable for installation over Everlay; not suitable for areas subject to impacts )		
<b>Subfloor Preparation</b>	Please refer to Mondo's Subfloor Preparation Guidelines		
<b>Installation</b>	Please refer to Manufacturer's Current Installation Guidelines		
<b>Maintenance</b>	Please refer to Manufacturer's Current Maintenance Guidelines		
<b>Environmental Data</b>			
<b>L.E.E.D. ® Contributions</b>			
Post-Consumer Recycled Content	76% by weight	1.87 lbs/sqft	9.12 Kg/sqm
Pre-Consumer Recycled Content	0% by weight	0.00 lbs/sqft	0.00 Kg/sqm
Rapidly Renewable Materials Content	3% by weight	0.08 lbs/sqft	0.38 Kg/sqm
<b>Technical Data</b>	<b>Test Method</b>	<b>Unit</b>	<b>Average Values</b>
Thickness	-	mm	<b>10 ± 0.2</b>
Weight	-	Kg/m <sup>2</sup>	<b>12 ± 5%</b>
Tensile Strength	ASTM D412	psi	<b>≥ 200</b>
Hardness of Top Layer	ASTM D2240	Shore "A"	<b>70 ± 5</b>
Hardness of Bottom Layer	ASTM D2240	Shore "A"	<b>65 ± 5</b>
Abrasion Resistance Taber (H18 Wheel 1000 cycles 1000g load)	ASTM D3389	gr weight loss	<b>≤ 0.8</b>
Static Load Limit (250 Lbs)	ASTM F970	Inches	<b>≤ 0.009</b>
Coefficient of Friction*1	ASTM D2047	-	<b>≥ 0.8</b>
Fungal Resistance Test	ASTM G21	-	<b>No Growth</b>
Chemical Resistance	ASTM F925	-	<b>No Surface Attack</b>
Critical Radiant Flux	ASTM E 648	W/cm <sup>2</sup>	<b>≥ 0.45 Class 1</b>
Optical Smoke Density	ASTM E662	-	<b>&lt; 450</b>
<b>Restrictions</b>	Not recommended for skate areas		
<b>Notes</b>	*1 OSHA Requires Coefficient of Friction > 0.5 ADA Requires Coefficient of Friction > 0.6 for Flat Surfaces, > 0.8 for Ramps		